

BRONZE BUSHING AB2 (ALUMINIUM BRONZE)

Colour Code	
-------------	--

Silver/Green (Bar End)	
------------------------	--

Related Specifications	
Australia	AS1565-1985-C95810
Germany	
Great Britain	BS1490 AB2
International	
Japan	
USA	

Typical Composition		
	Min. %	Max. %
Aluminium	8.50	9.50
Tin		0.10
Manganese	0.80	1.50
Nickel	4.00	5.00
Copper	79.00	
Lead		0.05
Iron	3.50	4.50

Interloy believes the information provided is accurate and reliable. However no warranty of accuracy, completeness or reliability is given, nor will any responsibility be taken for errors or omissions.